

TECHNICAL DATA SHEET

1. Name of the product: **CLEARIRTEC PG76**

2. Description

Clear synthetic binder with high performances. It could be coloured introducing some pigments during its employment.

3. Technical Characteristics

| Characteristics | Unit | Norm UNE-EN | Specification | |
|----------------------------------|--------|-------------------|---------------|-----|
| | | | Min. | Max |
| Original Binder | | | | |
| Penetration (25°C; 100g; 5s) | 0,1 mm | UNE-EN 1426 | 35 | 50 |
| Softening Point (Ring & Ball) | °C | UNE-EN 1427 | 75 | |
| Fraass Fragility point | °C | UNE-EN 12593 | | -10 |
| G*/sen δ 76°C at 10 rad/s | kPa | AASHTO TP5/93 | 1,0 | |
| Flash point | °C | ISO 2592 | 230 | |
| After Aging Process | | | | |
| Difference in mass | % | UNE-EN 12607-1 | | 0,5 |
| G*/sen δ 76°C at 10 rad/s | kPa | AASHTO TP5/93 | 2,2 | |

4. Use conditions

It is necessary to follow all prescription recommended in the Safety Data Sheet.

The information contained herein is indicative only and without express guarantee. As no control can be exercised over its use, we cannot be held responsible for any damage which may result from its misuse.

