

CLEARIRTEC PG76

DESCRIPTION:

DOPIRTEC AK is an adhesion promoter exempt from solvents used in hot mix asphalts, with the purpose to guarantee a perfectly stable tie between bitumen and aggregates independently from their chemical nature (acid or basic)

DOPIRTEC AK is avoiding stripping and raveling phenomena.

DOPIRTEC AK is stable at high storage temperature of bitumen (180°C) and even to extended heating time without changing its chemical characteristics. Stable at room temperatures if stored in closed containers and at shadow.

USE CONDITIONS:

It is necessary to follow all prescription recommended in the Safety Data Sheet.

TECHNICAL CHARACTERISTICS: STORAGE:

Characteristics	Unit	Norm UNE-EN	Specifications	
			min	max
Penetration (25°C; 100g; 5s)	0,1 mm	UNE-EN 1426	35	50
Softening Point (Ring & Ball)	°C	UNE-EN 1427	75	
Fraass Fragility point	°C	UNE-EN 12593		-10
G*/sen δ 76°C at 10 rad/s	kPa	AASHTO TP5/93	1,0	
Flash point	°C	ISO 2592	230	
After Aging Process				
Difference in mass	%	UNE-EN 12607- 1		0,5
G*/sen δ 76°C at 10 rad/s	kPa	AASHTO TP5/93	2,2	

The information contained herein is indicative only and without express guarantee. As no control can be exercised over its use, we cannot be held responsible for any damage which may result from its misuse.



The information contained herein is indicative only and without express guarantee. As no control can be exercised over its use, we cannot be held responsible for any damage which may result from its misuse.